

# ZISAMIDE®

## POLYAMIDE 6

Properties	Unit	TP4208	TP4407	TP6603	TP6802
含水量 Moisture content	ppm	< 1000	< 1000	< 1000	< 600
胺基 Amino end group	meq/kg	44 ± 3	51 ± 3	39 ± 3	31 ± 3
可萃取物 Extractable	% Max	< 0.6	< 0.6	< 0.6	< 0.6
熔點 Melting point	°C	220 ~ 225	220 ~ 225	220 ~ 225	220 ~ 225
流動率 Melt flow index	g/10min	180 ~ 230	70 ~ 125	30 ~ 60	15 ~ 35
應用範圍 Suitable application		Compounding Injection		Compounding Extrusion	

Packaging: 800 kgs Jumbo Bag <16 mt / 20' Container>

25 kgs Paper Bag <15 mt / 20' Container>

2016