

ZISAMIDE®

POLYAMIDE 6

Properties	Unit	HP1101	HP2201	HP3207	HP3402
含水量 Moisture content	ppm	< 600	< 600	< 600	< 600
胺基 Amino end group	meq/kg	44 ± 3	44 ± 3	44 ± 3	41 ± 3
可萃取物 Extractable	% Max	< 0.6	< 0.6	< 0.6	< 0.6
二氧化鈦 TiO ₂	%	0.3 ± 0.02	1.50 ± 0.10	-	-
熔點 Melting point	°C	220~225	220~225	220~225	220~225
流動率 Melt flow index	g/10min	200~250	190~240	210~260	70~120
應用範圍 Suitable application		Textile Semidull	Textile Fulldull	Textile Bright	Textile Bright

Packaging: 800 kgs Jumbo Bag <16mt / 20' Container>
25 kgs Paper Bag <15mt / 20' Container>

2016