

Vydyne® 20NSP1 polyamide 66



Vydyne 20NSP1 product description to come.

To come

Typical Applications/End Uses:

General				
Material Status	• Commercial: Active			
Availability	• Asia Pacific	• Europe	• North America	
Additive	• Lubricant	• Nucleating Agent		
Features	• Fast Molding Cycle • General Purpose • Good Mold Release	• Good Stiffness • High Rigidity • Lubricated	• Nucleated	
Uses	• Bearings • Cams • Connectors	• Fasteners • General Purpose • Housings	• Industrial Applications	
Agency Ratings	• ASTM D 4066 PA0131 • ASTM D 6779 PA0131 • EC 1935/2004	• EU 10/2011 • EU 2023/2006 • FDA 21 CFR 177.1500	• FED L-P-410A	
RoHS Compliance	• RoHS Compliant			
UL File Number	• E70062			
Appearance	• Natural Color			
Forms	• Pellets			
Processing Method	• Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.6	--	%	
Flow : 23°C, 2.00 mm	1.4	--	%	
Water Absorption (23°C, 24 hr)	1.2	--	%	ISO 62
Water Absorption (Equilibrium, 23°C, 50% RH)	2.4	--	%	ISO 62
Outdoor Suitability	f2	--		UL 746C

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3800	2500	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	95.0	60.0	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	75.0	50.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	5.0	15	%	ISO 527-2
Nominal Tensile Strain at Break (23°C)	13	20	%	ISO 527-2
Flexural Modulus (23°C)	3200	1300	MPa	ISO 178
Flexural Strength (23°C)	100	35.0	MPa	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	5.0	5.0	kJ/m ²	
23°C	6.0	15		
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Notched Izod Impact Strength				ISO 180
-30°C	5.0	5.0	kJ/m ²	
23°C	6.0	15	kJ/m ²	

指南者尼龙

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature 0.45 MPa, Unannealed	230	--	°C	ISO 75-2/B
Heat Deflection Temperature 1.8 MPa, Unannealed	90.0	--	°C	ISO 75-2/A
Melting Temperature	260	--	°C	ISO 11357-3
CLTE - Flow (23 to 55°C, 2.00 mm)	1.0E-4	--	cm/cm/°C	ISO 11359-2
CLTE - Transverse (23 to 55°C, 2.00 mm)	1.0E-4	--	cm/cm/°C	ISO 11359-2
RTI Elec				UL 746
0.71 mm	130	--	°C	
1.5 mm	130	--	°C	
3.0 mm	130	--	°C	
RTI Imp				UL 746
0.71 mm	75.0	--	°C	
1.5 mm	75.0	--	°C	
3.0 mm	75.0	--	°C	
RTI Str				UL 746
0.71 mm	85.0	--	°C	
1.5 mm	85.0	--	°C	
3.0 mm	85.0	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.750 mm)	1.0E+13	--	ohms-cm	IEC 60093
Dielectric Strength (1.00 mm)	26	--	kV/mm	IEC 60243
Arc Resistance (3.00 mm)	PLC 5	--		ASTM D495
Comparative Tracking Index (3.00 mm)	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.71 mm	PLC 0	--		
1.5 mm	PLC 0	--		
3.0 mm	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 0	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.71 mm	PLC 4	--		
1.5 mm	PLC 3	--		
3.0 mm	PLC 2	--		

Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.71 mm	V-2	--		
1.5 mm	V-2	--		
3.0 mm	V-2	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.71 mm	960	--	°C	
1.5 mm	960	--	°C	
3.0 mm	960	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.71 mm	850	--	°C	
1.5 mm	850	--	°C	
3.0 mm	850	--	°C	
Oxygen Index	26	--	%	ISO 4589-2
Injection		Dry Unit		
Drying Temperature	< 70 °C			
Drying Time	1.0 to 3.0 hr			
Suggested Max Regrind	50 %			
Rear Temperature	260 to 280 °C			
Middle Temperature	270 to 285 °C			
Front Temperature	280 to 290 °C			
Nozzle Temperature	280 to 300 °C			
Processing (Melt) Temp	285 to 300 °C			
Mold Temperature	65 to 95 °C			

指南者尼龙

Notes

Typical properties: these are not to be construed as specifications.

¹ Typical properties: these are not to be construed as specifications.



North America

+1 888 927 2363

Europe

+32 10 608 600

Asia

+86 21 6340 3300

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations LLC makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations LLC be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations LLC makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.