

# Vydyne® 22HSP NT polyamide 66



Vydyne 22HSP NT product description to come.

General				
Material Status	• Commercial: Active			
Availability	• Asia Pacific	• Europe	• North America	
Additive	• Lubricant			
Features	• Abrasion Resistant • Chemical Resistant • Fast Molding Cycle • Gasoline Resistant	• General Purpose • Good Mold Release • Good Toughness • High Rigidity	• High Strength • Lubricated • Oil Resistant • Solvent Resistant	
Uses	• Bearings • Bushings	• Cams • Connectors	• Housings • Industrial Applications	
Agency Ratings	• ASTM D 4066 PA0121 • ASTM D 6779 PA0121	• FDA 21 CFR 177.1500 • FFD L-P-410A	• MIL M-20693B	
RoHS Compliance	• RoHS Compliant			
Automotive Specifications	• FORD WSK-M4D647-A • FORD WSK-M4D647-A Color: Black • GM GMP.PA66.005 • GM GMP.PA66.005 Color: Black	• GM GMP.PA66.018 Color: Natural • GM GMW15702 • GM QK 002921 Color: Natural • NISSAN PA66-INX-1	• SAE J1639 PA0121 Z6 • SAE J1639 PA0121 Z6 Color: Black	
UL File Number	• E70062			
Appearance	• Natural Color			
Forms	• Pellets			
Processing Method	• Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	2.0	--	%	
Flow : 23°C, 2.00 mm	2.2	--	%	
Water Absorption (23°C, 24 hr)	1.2	--	%	ISO 62
Water Absorption (Equilibrium, 23°C, 50% RH)	2.4	--	%	ISO 62

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3100	1800	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	85.0	55.0	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	55.0	40.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	5.0	20	%	ISO 527-2
Nominal Tensile Strain at Break (23°C)	25	> 50	%	ISO 527-2
Flexural Modulus (23°C)	2900	1000	MPa	ISO 178
Flexural Strength (23°C)	95.0	30.0	MPa	ISO 178
Poisson's Ratio	0.40	--		ISO 527
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	5.0	7.0	kJ/m <sup>2</sup>	
23°C	6.0	20	kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Notched Izod Impact Strength				ISO 180
-30°C	5.0	7.0	kJ/m <sup>2</sup>	
23°C	6.0	20	kJ/m <sup>2</sup>	

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature 0.45 MPa, Unannealed	200	--	°C	ISO 75-2/B
Heat Deflection Temperature 1.8 MPa, Unannealed	70.0	--	°C	ISO 75-2/A
Melting Temperature	260	--	°C	ISO 11357-3
CLTE - Flow (23 to 55°C)	1.0E-4	--	cm/cm/°C	ISO 11359-2
CLTE - Transverse (23 to 55°C)	1.0E-4	--	cm/cm/°C	ISO 11359-2
RTI Elec				UL 746
0.71 mm	140	--	°C	
1.5 mm	140	--	°C	
3.0 mm	140	--	°C	
RTI Imp				UL 746
0.71 mm	95.0	--	°C	
1.5 mm	110	--	°C	
3.0 mm	110	--	°C	
RTI Str				UL 746
0.71 mm	115	--	°C	
1.5 mm	125	--	°C	
3.0 mm	125	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Arc Resistance (3.00 mm)	PLC 6	--		ASTM D495
Comparative Tracking Index (3.00 mm)	400 to 599	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.71 mm	PLC 0	--		
1.5 mm	PLC 0	--		
3.0 mm	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 0	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.71 mm	PLC 4	--		
1.5 mm	PLC 4	--		
3.0 mm	PLC 4	--		

Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (2.00 mm, Self-Extinguishing)	0.0	--	mm/min	ISO 3795
Flame Rating				UL 94
0.71 mm	V-2	--		
1.5 mm	V-2	--		
3.0 mm	V-2	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.71 mm	825	--	°C	
1.5 mm	825	--	°C	
3.0 mm	960	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.71 mm	700	--	°C	
1.5 mm	700	--	°C	
3.0 mm	700	--	°C	
Oxygen Index	24	--	%	ISO 4589-2
Injection		Dry Unit		
Drying Temperature	< 70 °C			
Drying Time	1.0 to 3.0 hr			
Suggested Max Regrind	50 %			
Rear Temperature	260 to 280 °C			
Middle Temperature	270 to 285 °C			
Front Temperature	280 to 290 °C			
Nozzle Temperature	280 to 300 °C			
Processing (Melt) Temp	285 to 300 °C			
Mold Temperature	65 to 95 °C			

**Notes**

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Typical properties: these are not to be construed as specifications.



**North America**

+1 888 927 2363

**Europe**

+32 10 608 600

**Asia**

+86 21 6340 3300

**Disclaimer of Warranty and Liability**

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations LLC makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations LLC be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations LLC makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.