

Vydyne® 50BW

polyamide 66



Vydyne 50BW is general-purpose PA66 resin. Offered in natural and designed for extrusion-compounding applications, this product is available at two moisture levels: 0.2% (max) as Vydyne 50BW and 0.5% (max) as Vydyne 50BWFS.

Vydyne 50BW provides the chemical resistance typical of PA66 to many chemicals, machine and motor oils, solvents and gasoline. Vydyne 50BW exhibits good initial color and color retention after compounding.

General			
Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Chemical Resistant • Gasoline Resistant	• General Purpose • Good Color Stability	• Oil Resistant • Solvent Resistant
Uses	• Compounding	• General Purpose	
Agency Ratings	• ASTM D 4066 PA0111 • ASTM D 3779 PA0111 • EC 1935/2004	• EU 10/2011 • EU 2023/2006 • FDA 21 CFR 177.1500	• NSF STD-51
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Compounding	• Compounding Extrusion	

Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Viscosity Number (H ₂ SO ₄ (Sulphuric Acid))	137 to 148	cm ³ /g	ISO 307
Bulk Density	675	g/l	ASTM D1895
Moisture Content	0.20	%	ASTM D6869
Relative Viscosity ²	45.0 to 51.0		ASTM D789

Thermal	Nominal Value	Unit	Test Method
Melting Temperature	260	°C	ISO 11357-3

Optical	Nominal Value	Unit	Test Method
Yellowness Index	-4.0	YI	ASTM D1925

Notes

Typical properties: these are not to be construed as specifications.

¹ Typical properties: these are not to be construed as specifications.

² Formic acid



North America

+1 888 927 2363

Europe

+32 10 608 600

Asia

+86 21 6340 3300

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations LLC makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations LLC be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations LLC makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.