

Vydyne® 52BWMS

polyamide 66



Vydyne 52BWMS is a medium-viscosity resin used for extrusion-compounding. It is the product of choice for low-yellowness-required applications. This product with its higher viscosity is a part of the 50BW/50BWFS series. It provides melt

stability during the compounding step to maintain its flow. Resistance of Vydyne 52BWMS to heat, oil and wear is typical of PA66 neat resins.

General			
Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Chemical Resistant • Gasoline Resistant	• General Purpose • Good Color Stability	• Oil Resistant • Solvent Resistant
Uses	• Compounding	• General Purpose	
Agency Ratings	• ASTM D 4066 PA0111 • ASTM D 3779 PA0111	• EC 1935/2004 • EU 10/2011	• EU 2023/2006 • FDA 21 CFR 177.1500
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Compounding	• Compounding Extrusion	

Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Viscosity Number (H ₂ SO ₄ (Sulphuric Acid))	146 to 153	cm ³ /g	ISO 307
Bulk Density	674	g/l	ASTM D1895
Moisture Content	0.35	%	ASTM D6869
Relative Viscosity ²	50.0 to 54.0		ASTM D789
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	260	°C	ISO 11357-3
Optical	Nominal Value	Unit	Test Method
Yellowness Index	-4.0	YI	ASTM D1925

Notes

Typical properties: these are not to be construed as specifications.

¹ Typical properties: these are not to be construed as specifications.

² Formic acid



North America

+1 888 927 2363

Europe

+32 10 608 600

Asia

+86 21 6340 3300

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations LLC makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations LLC be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations LLC makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.